



8708 W. Little York Road – Suite170 Houston TX 77040 USA  
 281-416-4449 Office or contact us info@impexglobalfilms.com

**TECHNICAL DATA SHEET**

**UNORIENTED CAST PP FILM FOR GENERAL APPLICATION**

**CCP - PT** : General Application

**CP – LT**: Low Temperature Hot- seal

**CCP - UL** : Ultra- low Temperature Heat- seal

**CCP - ET**: Extruded Lamination

**CCP- PT**

High transparency, good rigidity and excellent slip property of non- treated side. Good heat sealability.

**CCP- LT**

High transparency, good rigidity and excellent slip property of un- treated side. Low initial heat seal temperature.

**CCP- UL**

High transparency, good rigidity and excellent slip property of non- treated side. Low initial heat seal temperature.

**CCP- ET**

High transparency, good rigidity and excellent slip property of non- treated side. Suitable for extruded lamination with LDPE.

**TECHNICAL SPECIFICATIONS**

PROPERTIES	UNITS	CCP- PT	CCP- LT	CCP- UL	CCP- ET
Thickness	micron	30	25	20	30
	gauge	120	100	80	120
Tensile strength	MD	70	75	78	60
	TD	35	40	40	30
Elongation at Break	MD	420	450	680	620
	TD	550	550	800	830
Density	gms/ cm <sup>3</sup>	0.90	0.90	0.90	0.90
Haze	%	3.0	2.5	2.3	5.0
Initial Heat Seal temperature	°C	120	113	105	120
	° F				
Wet Tension ( Treated Side )	Mn/M	38	38	37	37
C.O.F					
Static		0.35	0.35	0.35	0.35
Dynamic		0.30	0.30	0.30	0.30

**SPECIFICATIONS**

Type	Thickness (um)	Width ( mm )	Roll Diameter ( mm )
PT, LT, UL, ET	20 – 60	300- 1500	300 – 500

MD Machine direction

TD Transverse direction

**NOTE:**



The above-mentioned data have been obtained using standard test procedures on defined specimens, and are provided in good faith. These results should therefore be regarded only as a general guide to material properties. It is for the customer to determine / decide a product's suitability for his / her own particular purpose. **IMPEX GLOBAL FILMS** does not claim and responsibility of the product for any particular purpose.