



8708 W. Little York Road – Suite170 Houston TX 77040 USA
 281-416-4449 Office or contact us info@impexglobalfilms.com

TECHNICAL DATA SHEET

BOPP FILM HAVING A CORONA TREATED WHITE CAVITATED PEARLESCENT SIDE AND SOLID WHITE APPEARANCE ON ITS OPPOSITE SIDE TWO SIDE HEAT SEALABLE

PBW

Coextruded film cavitated in its core, intended for printing applications to substitute the utilization of white ink. It is recommended in food packaging application, particularly, in cases where packaged food requires protection against sunlight.

Technical Specifications

PROPERTIES		UNITS	VALUES		TEST CONDITIONS
Thickness		mil	1.2	1.4	DIN 53370
		micron	30	35	
Unit Weight		lb/ream	12.5	14.6	ASTM D 2673 DIN 53352
		g/m ²	20.4	23.8	
Yield		in ² /lb	34,500	29,500	ASTM D2673 DIN 53352
		m ² /kg	49.0	42.0	
Coefficient of Friction			0.35		DIN 53375
Kinetic NT/ NT					
Treatment Level		dynes/ cm	38		ASTM D 2578
Seal Strength		gms/ inch N/15MM	650		IMP 01, 234 °F, 1 SEC, 14 psi IMP 01, 112° C, 1 Sec, 1 bar
			4		
Seal Initial Temperature (SIT)	NT/ NT		221		IMP 03
			105		
Dimensional Stability	MD	%	4.0		IMP 0 02, 120 °C, 5 min IMP 0 02, 120 °C, 5 min
	TD	%	2.0		
Opacity		%	80		ASTM D 1003
Gloss (45°)			50		ASTM D 2457
			90		
Tensile Strength	MD	lb/in ²	11,500		ASTM D 882 DIN 53455
		N/mm ²	80		
	TD	lb/in ²	19,000		
		N/mm ²	130		
Elongation at break	MD	%	130		ASTM D 882 DIN 53455
	TD	%	50		

MD Machine direction

TD Transverse direction

NT/NT Non Treated Side/Non Treated Side

NOTE:



The above-mentioned data have been obtained using standard test procedures on defined specimens, and are provided in good faith. These results should therefore be regarded only as a general guide to material properties. It is for the customer to determine / decide a product's suitability for his / her own particular purpose. **IMPEX GLOBAL FILMS** does not claim and responsibility of the product for any particular purpose.