



8708 W. Little York Road – Suite170 Houston TX 77040 USA
 281-416-4449 Office or contact us info@impexglobalfilms.com

TECHNICAL DATA SHEET

CPP TWIST FILM

TCP

Perfect twist and stiffness property
 Good transparency and gloss
 Strong metallized layer adhesion
 Good humidity resistance
 Recyclable.

This kind of film can be used directly or after aluminum deposition as twist package for food package such as candles with the distinguished visual aesthetic and decorative effect. They can partially replace PVC twist film for environment friendly purpose and low cost

Technical Specifications

Properties	Test	Units	Values
Thickness	GB 6672	micron	30
Tensile strength MD TD	GB 13022	Mpa	70 60
Elongation at Break MD TD	GB 13022 GB 13022	% %	500 600
Heat Seal Strength (135°C)	GB/T 28004	N/15 mm	10.0
Haze	GB 2410	%	2.0
Gloss	GB 8807	%	90
Wet Tension	GB/T 14216	MN/ m	40

Roll Specifications

Thickness (um)	Width (mm)	Roll Diameter (mm)
20 ~50	500 ~1500	300 - 500

MD Machine direction
 Transverse direction

NOTE:



The above-mentioned data have been obtained using standard test procedures on defined specimens, and are provided in good faith. These results should therefore be regarded only as a general guide to material properties. It is for the customer to determine / decide a product's suitability for his / her own particular purpose. **IMPEX GLOBAL FILMS** does not claim and responsibility of the product for any particular purpose.